

Technical Data Sheet



ORF PU Binder ODST - 43

Page 1 of 1
Date: 01 – 11 - 22

Application

- ORF Binder ODST - 43 is an un-pigmented single component, solvent free, polyurethane binder.
- ORF Binder ODST - 43 is a slow curing PU binder stone aggregates application.

Properties

- The ORF Binder ODST - 43 has a low viscosity and mixes very easy with the Stone and Pebbles.
- ORF Binder ODST – 43 is an aromatic binder (not UV stable).

Packaging & Colours

- ORF PU Binder ODST - 43 is available in 210 kg drums. And it is colourless.

Storage

- Store in original containers, under dry conditions.
- Do not expose to direct sunlight. Protect from frost.
- Shelf Life Approx. 6 Months if stored correctly.

Component Data

Characteristics	Unit	Value	Method
Density (25°C)	g/cm ³	1050	ASTM - D1475
Viscosity (25°C)	mPa-s	2707	ASTM - D5125
Shelf-life	months	6	

Our recommendations concerning the technical application of the product, whether through oral or written communication or through demonstration, are given to the best of our current knowledge; however, any such instruction shall be without commitment, including where any protective rights of third parties are involved. They do not free you of the obligation to check the products supplied by us for their suitability for the procedures and applications envisaged. The (intended) use and application of the products are beyond our control. They are therefore your personal responsibility. In the event that ORF proves liable, such liability shall be limited in all cases of damage to a sum not exceeding the actual value of the goods supplied by us and used by you. It goes without saying that we guarantee the good quality of our products, in accordance with the standards set out in our

General Terms of Sale and Delivery.